


SPECTRUM PRO SHINY SPEC TEST RESULTS

Color fastness values - AATCC standards



NAME	COLOR CODE	WASHING (C.C)	WASHING (C.S)	COLD WATER (C.C)	COLD WATER (C.S)	ACID PERSPIRATION (C.C)	ACID PERSPIRATION (C.S)	SEA WATER (C.C)	SEA WATER (C.S)	CHLORINATED WATER (C.C)	LIGHT
RED	TTS650C3	4	4	4	4	4	4	4	4	4	4
MAROON	TTS650C30	4	3.5	4	4	4	4	4	4	4	4.5
CINNAMON	TTS650C18	4	3.5	4	4	4	4	4	4	3.5	4.5
GOLD	TTS650C12	4	4	4	4	4	4	4	4	4	4
LIGHT BLUE	TTS650C17	4	4	4	4	4	4	4	4	2	4.5
TURQUOISE	TTS650C14	3.5	4	4	4	3.5	4	3.5	4	4	2.5
ROYAL	TTS650C33	4.5	4.5	4.5	4.5	4.5	4	4.5	3	4	4
NAVY	TTS650C29	4	4.5	4.5	3	4.5	3.5	4.5	3.5	4	4
BLACK	TTS650C1	4	3.5	4	3.5	4	3.5	4	3.5	4	4
HOT PINK	TTS650C13	3	3.5	4	2.5	3	2.5	2.5	3	2.5	1.5
PURPLE	TTS650C28	4	4	4	4	4	4	4	4	3.5	4.5

SPECTRUM PRO SHINY TRICOT	
CONTENT	83% NYLON 17% SPANDEX
WIDTH	57/59"
WEIGHT	6.00Z/SQ. YD (205G/SQ. M)
STRETCH WIDTH	95 (+/-15%)
STRETCH LENGTH	140 (+/-15%)



All tested colors have been rated at 50+ blocks 99-100% of all ultraviolet rays.